



THE BEST CORROSION CONTROL PERFORMANCE, GUARANTEED!

## **Termarust® TR2010RI High Ratio Co-Polymerized Calcium Sulfonate Flash Rust Inhibitor**

|   |  |
|---|--|
| <b>DESCRIPTION</b>                                  | Flash rust inhibitor.  |
| <b>USES</b>   | For application on newly blasted, non contaminated steel surfaces, to hold and preserve blast for several days against flash rust corrosion. |
| <b>COLOR</b>  | Light Tan  |
| <b>SHEEN</b>  | Low Gloss  |
| <b>COMPATIBLE SYSTEMS</b>                           | Termarust® TR2100 Primer/Topcoat, Termarust® TR2200 Penetrant/Sealer   |
| <b>RESIN TYPE</b>                                   | High Ratio Co-Polymerized Calcium Sulfonate  |
| <b>SOLVENT</b>                                      | Mineral spirits  |
| <b>SOLIDS BY WEIGHT</b>                             | 10% +/- 1%   |
| <b>SOLIDS BY VOLUME</b>                             | 7.5% +/- 1%  |
| <b>V.O.C. (VOLATILE ORGANIC COMPOUND)</b>           | 720 grams per litre  |
| <b>RECOMMENDED DFT (DRY FILM THICKNESS)</b>         | 2.5 microns - 0.25 mils  |
| <b>DRY TIME @ 25°C - 50% RH (relative humidity)</b> | TACK FREE: 15 minutes<br>RECOAT: 15 minutes  |
| <b>SURFACE PREPARATION</b>                          | Sandblast surface. Do not apply on contaminated surface.   |
| <b>APPLICATION</b>                                  | Apply by spray. Excess coating should be brushed out or blown away and no pooling shall be allowed.  |

314 AYITO ROAD SE, VIENNA, VA 22180-5983, FAX 703-938-1252  
9100 EDISON, ANJOU (MONTREAL), QUEBEC H1J 1T3, FAX 514-354-2799

TOLL FREE 1-888-279-5497

info@termarust.com / www.termarust.com



THE BEST CORROSION CONTROL PERFORMANCE, GUARANTEED!

|                           |   |                            |
|---------------------------|---|----------------------------|
| <b>THINNING</b>           | Spray:  | No thinning required.      |
|                           | Clean Up:   | Use Ferox mineral spirits. |
| <b>PERFORMANCE</b>        | Will hold and preserve blast for one week. In some cases, Termarust® TR2010RI has held a blast for 60 days.   |                            |
| <b>SHELF LIFE</b>         | 12 months or longer in original unopened container when stored in a protected area where the temperature is between 5°C and 30°C (41°F - 86°F).   |                            |
| <b>SAFETY INFORMATION</b> | Treat as flammable liquid - Flash point 42°C (108°F). Keep away from heat, open flame and sparks. Avoid contact with skin and eyes. Avoid prolonged breathing of vapor. <b>Read label instructions carefully and refer to Material Safety Data Sheet</b> supplied.  |                            |
|                           | This product is for <b>industrial use only</b> and is not intended for use in or around a household or dwelling.  |                            |
| <b>NOTE</b>               | The technical data given herein has been compiled for your help and guidance and is based upon our experience and knowledge. It is subject to modification from time to time in the light of experience and our policy of continuous product development. Persons using this product must first satisfy themselves as to its suitability for the intended purpose. Please contact your representative for complete recommendations. |                            |
|                           | A complete Termarust® TR2010RI Flash Rust Inhibitor application specification is available upon request.  |                            |

---

314 AYITO ROAD SE, VIENNA, VA 22180-5983, FAX 703-938-1252  
9100 EDISON, ANJOU (MONTREAL), QUEBEC H1J 1T3, FAX 514-354-2799

TOLL FREE 1-888-279-5497

[info@termarust.com](mailto:info@termarust.com) / [www.termarust.com](http://www.termarust.com)